

# LOCTITE EO7021

January 2014

## PRODUCT DESCRIPTION

LOCTITE EO7021 provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Appearance</b>	Black
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• One component</li> <li>• Low viscosity</li> <li>• Fast cure at moderate temperatures</li> </ul>
<b>Cure</b>	Heat cure
<b>Application</b>	Encapsulant, Coating

LOCTITE EO7021 encapsulant is designed for use in smart card chip module applications. It is also suitable for die attach automated reel-to-reel processing .

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity, Epprecht , 25 °C, mPa·s (cP):	
Spindle D, speed 5 rpm	17,000
Specific Gravity @ 25°C, g/cm <sup>3</sup>	1.19
Shelf Life @ 5°C (from date of manufacture), days	270
Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

<b>Gel Time</b>	
@ 100°C, minutes	15
@ 110°C, minutes	7
@ 120°C, minutes	4

### Recommended Cure for Reel-to-Reel Processing

Substrate and Chip Module Preheat, °C	100
Precure	3 minutes @ 140°C
Postcure (after reel is completely full)	16 hours @ 100°C

### Alternate Cure for Reel-to-Reel Processing

Precure	1 hour @ 100°C
Postcure	6 hours @ 120°C

These applies only to coating chip module with 10 to 100 mg of LOCTITE EO7021.

### Recommended Cure for Non-Conductive Die Attach Application

1 hour @ 120°C or
5 minutes @ 150°C

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

All measurements are taken at room temperature unless otherwise noted.

### Physical Properties

Glass Transition Temperature (Tg) by TMA, °C	125
Coefficient of Linear Thermal Expansion , TMA, ppm/°C:	
Alpha 1, 40 to 100 °C	67
Alpha 2, 160 to 200 °C	187
Hardness, , Shore D, DIN 53505, Minimum	83
Tensile Modulus , ASTM D638	N/mm <sup>2</sup> 1,447 (psi) (210,000)
Flexural Modulus , ASTM D790	N/mm <sup>2</sup> 3,364 (psi) (488,000)
Elongation , ASTM D638,%	3.97
Thermal Conductivity, ASTM D1674	5.32×10 <sup>-4</sup>
Linear Shrinkage, ASTM D2566, %	0.73

### Electrical Properties

Volume Resistivity, 100 volts, ASTM D257, ohm-cm	1.98×10 <sup>17</sup>
Surface Resistivity, 100 volts, ASTM D257, ohm-cm	5.21×10 <sup>16</sup>
Arc Resistance, ASTM D495, seconds	88.7
Dielectric Constant , ASTM D150:	
@ 10Hz	3.682
@ 1KHz	3.666
@ 10KHz	3.627
@ 100KHz	3.556
Dissipation Factor, ASTM D150:	
@ 100Hz	0.0056
@ 1KHz	0.0063
@ 10KHz	0.0089
@ 100KHz	0.016

## TYPICAL PERFORMANCE OF CURED MATERIAL

Tensile Strength , ASTM D638	N/mm <sup>2</sup> 48 (psi) (7,000)
Flexural Strength, ASTM D790	N/mm <sup>2</sup> 0.105 (psi) (15.3)

## GENERAL INFORMATION

**For safe handling information on this product, consult the Safety Data Sheet, (SDS).**

### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

### THAWING:

1. Allow container to reach room temperature before use.

**DIRECTIONS FOR USE**

1. LOCTITE EO7021 should not be used for potting or globbing masses larger than 1 gram when curing at more than 120°C. Severe exotherm may occur and can cause bubble formation, craters on the surface, smoke and high shrinkage. Pre-curing at 100°C or 110°C will encounter these disadvantages.
2. Mix thoroughly before use. Heating to 40°C will lower the viscosity and aid in mixing and pouring (the viscosity will remain the same for a few hours).

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage : 10 °C or lower**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{psi} \times 145 = \text{N/mm}^2$$

$$\text{MPa} = \text{N/mm}^2$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference **N/A**