

Thermal Interface Materials

PTM7950


High Thermal Conductivity Phase Change Material

Honeywell's PTM7950 series, a super highly thermally conductive Phase Change Material (PCM) in both pad and paste formats, is designed to minimize thermal resistance at interfaces, maintain excellent performance through reliability testing, and provide scalable application at a competitive cost.

Based on a novel polymer PCM system, this material exhibits excellent interface wetability during typical operating temperature ranges, resulting in extremely low surface contact resistance.

A proprietary material provides superior reliability (pass 150° C baking 1000 hours, T/C-B 1000 cycles) and maintains low thermal impedance (<0.04°Ccm2/W @ no shim), making the PTM7950 series desirable for high performance integrated circuit devices.

PTM7950 Thermal Impedance (TI) vs. Pressure



PTM7950 is ideal for high performance IT/Enterprise computing applications.

Honeywell TIMs Serve Multiple Applications



Automotive & Power



IT/Enterprise



Telecomm



Consumer Electronics



High-Brightness LED

FEATURES & BENEFITS

- High performance filler and polymer technology
- Phase change at 45°C
- Highly conductive filler loading to optimize performance
- Superior handling and reworkability
- Superior reliable thermal performance
- Available in both pad and paste formats

PTM7950 Technical Information

| Physical Properties | Unit | Test Method | PTM7950 | PTM7950-SP |
|--------------------------------|----------------------------------|------------------------|----------------------|----------------------|
| Thermal Conductivity | W/m·K | ASTM D5470 | 8.5 | 8.5 |
| Thermal Impedance @ no shim | °Ccm²/W | ASTM D5470 Modified | 0.04 | 0.04 |
| Specific Gravity | g/cm ³ | ASTM D374 | 2.8 | 2.5 |
| Viscosity | Pa·s @2 10 ₁ /s, 25°C | Rheometer HON | NA | 21 |
| Volume Resistivity | Ω -cm | ASTM D257-700 | 2.1x10 ¹⁴ | 2.1x10 ¹⁴ |
| Thickness Range | mm | | .25 | NA |



PTM7950 pad format. It is also available in paste/ printable format.

STORAGE CONDITION

Refer to product label.

THERMAL IMPEDANCE POST RELIABILITY (ASTM E1461)

 $\begin{array}{lll} \mbox{End of Line} & 0.04\,^{\circ}\mbox{C-cm2/W} \\ \mbox{Bake } 150\,^{\circ}\mbox{C, }1000\,\mbox{h} & 0.04\,^{\circ}\mbox{C-cm2/W} \\ \mbox{Double } 85, 1000\mbox{h} & 0.04\,^{\circ}\mbox{C-cm2/W} \\ \mbox{Temperature Cycling "B"} & 0.045\,^{\circ}\mbox{C-cm2/W} \end{array}$

(-55°C to +125°C, 1000 cycles)

Product Use

Clamping pressure and temperature are suggested to achieve a minimum bond line thickness of the thermal interface material, typically less than 1.5 mil (0.038mm) for best performance. The material must go through the phase change temperature to exhibit entitlement performance.

More Honeywell TIMs

PTM7950 is part of Honeywell's TIM Solutions family of phase change materials. Whatever the thermal challenge, we offer a TIM product that provides just the right characteristics for your application. Find out more about:

PTM7000 Series PTM6000 Series
PTM5000 Series PCM45F Series
HT Series LTM Series

By visiting: electronicmaterials.com



Honeywell Electronic Materials

USA: 1-509-252-2102 China: 86-21-28942481 Germany: 49-5137-999-9199 Japan: 81-3-6730-7092 Korea: 82-2-3483-5076

Singapore: 65-6580-3593
Taiwan: 886-3-6580300 ext.312
www.electronicmaterials.com

Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

DS.0318Rev1 ©2018 Honeywell International Inc.

