

LINQSHEET RCS 320

Rubber Cleaning Sheets



- Optical Cleaning performance
- Good flow characteristics
- No mold abrasion

RCS 320 Rubber cleaning sheets are used to eliminate pollutants and stains formed on the mold surface. They perform well in a wide range of molds, are able to withstand a torque of 10 lb-in to 45 lb-in and have a curing time of only 300-350 seconds. These sheets offer an **optimal cleaning performance** with less smell and fumes. Naturally sheets are **compression grade**; not like you can transfer clean with sheets but let's get this out of the way for anyone still confused with the cleaning process nomenclature.

RCS 320 sheets have good flow characteristics which enable them to **clean mold corners** and thin gate areas easily. Unlike melamine cleaners, RCS cleaning sheets can even clean the air ventilation areas without causing mold abrasion or corrosion. At the same time there's **no need for dummy lead frame or preheating**, something that reduces cleaning time and leads to improved production time results and productivity. Even though they should be sufficient for deep stains, you can combine them with 2 initial shots of RCS520 to soften annoying residues and get that extra oomph.

RCS 320 Rubber cleaning sheets are well suited for production lines that **work with Electromagnetic Compatibility** (EMC) AND can remove contamination of molds used in the semiconductor industry for products such as as integrated circuits, diodes, transistors, and LEDs in both physical and chemical mechanisms.

| Property | Value |
|------------------|----------------|
| Appearance | White |
| Specific Gravity | 1.1 ±0.05 g/cc |
| Min Torque | 10 lb-in |
| Max Torque | 45 lb-in |
| Solubility | Not Soluble |

| Parameter | Condition |
|------------------|---------------|
| Clamp Pressure | 30 - 150 T |
| Mold Temperature | 170 - 180 °C |
| Curing Time | 300 - 350 sec |
| Shots | 2+ shots |
| Fume time | 50 - 60 sec |

Storage and packaging

Rubber cleaning sheets should be kept cooled in a temperature below 5°C. Their shelf life in these storage conditions is 12 months. After taking them out of storage they have 4 days to be used before they lose their effectiveness.

They are packaged in PE bags and come in 10Kg (net) boxes. Exact width is not stated since the sheets can be arrayed for the application and width is adjusted to the box size to accommodate the net weight

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@capling.com

North America

957 Snowshoe Crescent
Orléans ON, K1C 2Y3
Canada
Phone: +1 (613) 482-2215
Email: info@capling.com



United States

847 Sumpter Road #5155
Detroit, MI 48111
United states
+1 (313) 558-8243
Email: info@capling.com

Asia

Minle Garden, Baoan dst
Shenzhen City - 51831
China
Phone: +86 1368608 1428
Email: info@capling.com