



TGA FOR PTM7950

PTM7950

June 9, 2023

Honeywell

TGA TEST RESULT FOR PTM7950

0706-PTM7950-7XT00521A5

Test description

- Start at room temperature
- Ramp 10°C/min
- Isothermal for 30min at 200°C

Test result

- ✓ 0.052% weight loss was observed during temperature ramping up.
- ✓ 0.060% weight loss was observed when sample was baking at 200°C for 30 min

