

LINQSTAT **XVCF-3S500**

Carbon filled polyethylene film



- 3 mil film
- Black color
- ± 500 ohms/sq Surface resistivity

LINQSTAT XVCF-3S500 is a highly conductive polyethylene film with a very high electrically conductive carbon loading and a very dense polymer mix. Using a premium polymer and a refined process, we are able to increase the conductivity and thus reduce the surface resistance of the plastic to as low as ± 200 ohms/sq of surface resistance. This extra loading allows the film to be used in applications that require a lower resistivity. Volume resistivity, based on the thickness of the material is around 25 ohms-cm.

XVCF-3S500 conductive film is thin, lightweight and relatively inert. Furthermore, it is well suited for applications requiring electrochemical reactions, high conductivity or charge storage including but not limited to electrodes (ECG, TENS, Defibrillation and Iontophoresis), batteries (flat-cell zinc/manganese dioxide (MnO_2), Lithium Ion and Lithium polymer), wearable electronics and digital whiteboards.

Specifications

Property	Value	Unit
Color	Black	-
Chemistry Type	Carbon-Loaded PE	-
Film Thickness	76.2 (3)	um (mil)
Surface Resistivity	± 500	ohms/sq
Volume Resistivity	± 3.5	ohms-cm
Tensile Strength	21.7	mPa
Elongation	103	%
Melting Temperature	115-130	°C
Thermal Conductivity	0.065	W/(mK)
Density	1.12	g/cm ³

Storage and Handling

Shelf life is 5 years if stored in a dry and cool, well ventilated place at room temperature.

The product is supplied in rolls and it's conductivity is unaffected by humidity and age. The film is heat sealable, flexible, and offers exceptional abrasion resistance.

Europe

Industrieweg 15E,
1566JN Assendelft
The Netherlands
Phone: +31 (20) 893 2224
Email: info@caplinq.com

Canada

80 Sirocco Crescent
Ottawa ON, K2S 2C9
Canada
Phone: +1 (613) 482-2215
Email: info@caplinq.com



North America

36927 Schoolcraft Rd
Livonia, MI 48150
United States
Phone: +1 (313) 558-8243
Email: info@caplinq.com

South East Asia

S-08-07 Persiaran Triangle
B Lepas, Penang 11900
Malaysia
Phone: +60 (12) 4302223
Email: info@caplinq.com