

LOCTITE ABLESTIK 563K

November 2019

PRODUCT DESCRIPTION

LOCTITE ABLESTIK 563K provides the following product characteristics:

Technology	Epoxy Film
Appearance	beige
Cure	Heat cure
Product Benefits	Thermally conductive
	Thin bondline
	Uniform bondline control
	Good heat transfer
Application	Assembly
Carrier Type	None
Film Thickness	50microns and 75microns

LOCTITE ABLESTIK 563K adhesive film is suitable for bonding "hot" devices onto heat sinks where electrical insulation and good heat transfer are required. It exhibits low squeeze out during bonding. This product provides high strength over a wider temperature range than is normally associated with flexible films.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Work Life @ 25°C, months	3
Shelf Life @ 5°C, months	6
Shelf Life @ -40°C, year	1
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

30 minutes @ 150°C

Alternate Cure Schedule

2 hours @ 125°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Coefficient of Thermal Expansion, ppm/°C:	
Below Tg	45
Above Tg	500
Glass Transition Temperature, °C	97
Thermal Conductivity @ 121°C, W/(m-K)	1.1

TYPICAL PERFORMANCE OF CURED MATERIAL

Lap Shear Strength:

Al to Al @ 25°C, psi 3,000

TYPICAL ENVIRONMENTAL RESISTANCE

Outgassing Properties

 Outgassing , NASA Outgassing:
 0.44

 TML, %
 0.04

 CVCM, %
 0.04

 WVR, %
 0.2

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

THAWING:

- 1. Allow material to reach room temperature before use.
- 2. DO NOT open the package before contents reach ambient temperature.
- 3. Any moisture that collects on the thawed package should be removed prior to opening the package.

DIRECTIONS FOR USE

- 1. LOCTITE ABLESTIK 563K adhesive film is unsupported.
- 2. Handle carefully to avoid any stretching or flexing when frozen.
- It may be helpful during handling to keep at least one sheet of release paper attached.
- 4. Preheat surface to be bonded to approximately 45°C.
- 5. Remove release paper from one side of the adhesive film.
- 6. Apply film to one of the bonding surfaces.
- 7. Smooth out any trapped air by gently pressing on the surface.
- 8. Allow device to cool to room temperature.
- 9. Remove the release paper from the other side of the adhesive film. Attach the remaining adherend.
- 10. Apply clamp to provide a continuous pressure of at least 1 psi during cure cycle.
- 11. Place assembly in a preheated oven and cure at the recommended cure schedule.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

LOCTITE ABLESTIK film products can be stored at -40°C for up to one year. The shelf life of the film is only valid when the material has been stored at the specified storage conditions. Incorrect storage conditions will degrade the performance of the material in final cured properties. Avoid flexing film when frozen.



Conversions

(°C x 1.8) + 32 = °F kV/mm x 25.4 = V/mil mm / 25.4 = inches N x 0.225 = lb/F N/mm x 5.71 = lb/in psi x 145 = N/mm² MPa = N/mm² N·m x 8.851 = lb·in N·m x 0.738 = lb·ft N·mm x 0.142 = oz·in mPa·s = cP

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 0.4