

# RCS 320

## Rubber Cleaning Sheets



- Optimal Cleaning performance
- Good flow characteristics
- No mold abrasion

**RCS 320** Rubber cleaning sheets are used to eliminate pollutants and stains formed on the mold surface. They perform well in a wide range of molds, are able to withstand a torque of 9 lb-in to 51 lb-in and have a curing time of only 250-350 seconds. These sheets offer an **optimal cleaning performance** with less smell and fumes.

**RCS 320** sheets have good flow characteristics which enable them to **clean mold corners** and thin gate areas easily. Unlike melamine cleaners, RCS cleaning sheets can even clean the air ventilation areas without causing mold abrasion or corrosion. At the same time there's **no need for dummy lead frame or preheating**, something that reduces cleaning time and leads to improved production time results and productivity.

**RCS 320** Rubber cleaning sheets are well suited for production lines that **work with Electromagnetic Compatibility** (EMC) AND can remove contamination of molds used in the semiconductor industry for products such as as integrated circuits, diodes, transistors, and LEDs in both physical and chemical mechanisms.

Property	Value
Appearance	White
Specific Gravity	1.1 ±0.05 g/cc
Min Torque	9 - 11 lb-in
Max Torque	49 - 51 lb-in
Solubility	Not Soluble

Parameter	Condition
Clamp Pressure	30 - 150 T
Mold Temperature	160 - 190 °C
Curing Time	250 - 350 sec
Shots	2+ shots
Fume time	50 - 60 sec

### Storage and packaging

Rubber cleaning sheets should be kept cooled in a temperature below 5°C. Their shelf life in these storage conditions is 12 months. After taking them out of storage they have 4 days to be used before they lose their effectiveness.

They are packaged in PE bags and come in 10Kg (net) boxes. Exact width is not stated since the sheets can be arrayed for the application and width is adjusted to the box size to accommodate the net weight

#### Europe

Industrieweg 15E,  
1566JN Assendelft  
The Netherlands  
Phone: +31 (20) 893 2224  
Email: info@caplinq.com

#### North America

957 Snowshoe Crescent  
Orléans ON, K1C 2Y3  
Canada  
Phone: +1 (613) 482-2215  
Email: info@caplinq.com



#### United States

847 Sumpter Road #5155  
Detroit, MI 48111  
United states  
+1 (313) 558-8243  
Email: info@caplinq.com

#### Asia

Minle Garden, Baoan dst  
Shenzhen City - 51831  
China  
Phone: +861368608 1428  
Email: info@caplinq.com