



PRODUCT DESCRIPTION

HYSOL GR180T provided the following product characteristics:

Technology	Epoxy
Cure	Heat cure
Appearance	White
Filler Type	Crystal silica
Filler Weight, %	70
Application	Molding compound
Target Package	Opto coupler
Product Benefits	Excellent workability High reliability High light transmittance

GR180T provides with excellent performance. This material has been specifically designed to improve light transmittance and workability property.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Spiral Flow, @175°C, inches	29
Gel Time, @175°C, seconds	15
Shelf Life, @ 5°C, months	12

TYPICAL PROCESS DATA

Handling	Typical Value
Preheat Temperature, conventional mold, °C	70~90
Molding Temperature, °C	160~180
Transfer Pressure, Kg/cm ²	40~85
Transfer Time @ 175°C, seconds	5~12
Hot Hardness, Shore D @ 175 °C, after 90sec	81
Curing Time @ 175 °C, seconds	100~120
Post Mold Cure @ 175 °C, hours	4~8

HYSOL GR180T has been formulated to provide the best possible moldability and as wide a molding latitude as possible. Although molding and curing conditions will vary from situation to situation, recommended starting ranges are shown above.

Please contact Hysol Huawei Technical Service for alternative process parameters if needed.

TYPICAL PROPERTIES OF CURED MATERIAL

All measurements are taken at 25°C unless otherwise noted.

All physical, electrical and analytical measurements are taken on specimens cured for **120 seconds @ 175°C** with post cure of 6 hours @ **175°C**, unless otherwise specified.

Physical Properties

Property	Typical Value
----------	---------------

Glass Transition Temperature, °C: (Tg) via TMA	195
Coefficient of Thermal Expansion, TMA, ppm/°C: Below Tg	26.0
Above Tg	67.5
Flexural Modulus @ 25°C, MPa	10075
Flexural Strength @ 25°C, MPa	90
Moisture Absorption, 24 hours PCT, %	0.67
Specific Gravity	1.85
Light transmittance @ 2mm, %	15

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact Hysol Huawei Electronics Co., Ltd. quality department for assistance and recommendations on specifications for this product

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 5°C or below, in closed containers. After removal from cold storage, the material **MUST** be allowed to come to room temperature, in the sealed container, to avoid moisture contamination. The suggested waiting time for a standard 15 kg carton box is 24 hours.

Material removed from containers may be contaminated during use. Do not return product to the original container. Hysol Huawei Electronics Co., Ltd. cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact Hysol Huawei Electronics Co., Ltd. Technical Service or Customer Service Representative.

Disclaimer

NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our best knowledge and experience of the product as at the date of this TDS. Hysol Huawei Electronics Co., Ltd. is, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical

Data Sheet regarding the concerned product is excluded.